

ALWA-MOULD D + ALWA-MOULD V for thermoforming moulds

Advantages:

All volumes and mould sizes, pre-backing is not necessary
Productions moulds within the same day
Easy handling
High shiny polish able and easily machine able

Processing:

System contents:

Release agents
Resin
Aluminium filler
Hardener



model (master pattern)



release agent



wires for vacuum holes



**mixing of resin + aluminium
powder and app. 60 min.
for degassing**



**mix the hardener at the
same time**



Pour in a thin stream



curing time app. 45 min.



**the mould is ready for
production at the same day**